

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 August 2003 (07.08.2003)

PCT

(10) International Publication Number
WO 03/065467 A1

(51) International Patent Classification²: H01L 39/14,
39/24

ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP,
KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD,
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,
SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ,
VN, YU, ZA, ZW.

(22) International Filing Date: 29 January 2002 (29.01.2002)

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

(25) Filing Language: English

Published:

- with international search report
- with amended claims

(26) Publication Language: English

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.


(71) Applicant and

(72) Inventor: MANNHART, Jochen, Dieter [DE/DE]; Edel-
weissring 46, 86321 Königsbrunn (DE).

(74) Agent: BARTH, Carl, Otto; Barth & Partner, Zürich-
strasse 34, CH-8134 Adliswil (CH).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE,

(54) Title: SUPERCONDUCTOR WITH OPTIMIZED MICROSTRUCTURE AND METHOD FOR MAKING SUCH A SUPER-
CONDUCTOR



(57) Abstract: The present invention concerns the improvement of the supercurrent carrying capabilities, i.e. the increase of critical current densities, of polycrystalline superconductor structures, especially of high- T_c -superconductors. By modifying the microstructure of the substrate or by appropriately influencing the buffer layers in coated conductors to obtain grains with large aspect ratios which are predominantly oriented along the direction of the current flow, grain boundaries with large areas are obtained in the polycrystalline superconducting film that can support large critical currents along the superconductor. Thereby large critical currents are obtained in the superconductor for a given spread of misorientation angles of the grains.

WO 03/065467 A1

BEST AVAILABLE COPY